

Borchi® Add 406WS

TECHNICAL DATA

Compatibilizer developed to improve color acceptance of universal tinting systems.

FEATURES

- Drastically reduces or eliminates rub-out of universal water-based concentrates in solvent-based alkyd bases
- Easy to use as a post-additive
- Improves compatibility
- 90% solid in water
- APEO- and VOC-free

PHYSICAL CHARACTERISTICS

Appearance	Light yellow, viscous liquid
Non-volatile content	89 - 91 %
pH	5 - 7 (aqueous solution 10 %)
Density	1.12 g/cm ³ , 20 °C
Viscosity	Max. 100s (DIN cup 6 mm) (23 °C)
Solvent(s)	NA

APPLICATIONS

- Universal water-based concentrates in solvent-based alkyd systems

DOSAGE

1 - 3 % active on basecoat

STORAGE

Protect from the effects of weather and store at temperatures between 5 and 30 °C. Once opened, containers should be resealed immediately after each removal of the product.

SAFETY

Please refer to our safety data sheet for information relating to product safety.

Contact us for more information

www.borchers.com/contact

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.

Borchi® Add Testing Plan

PHASE 1

1. Add each Borchi® Add product into the incompatible system individually.
 - a. Below is a table of test formulations.
 - i. Formulations are out of 100 for ease of calculation, but you can scale to whatever is appropriate for your equipment.
2. Mix/Agitate for 1 minute at 1500 rpm.
3. Drawdown the sample next to a control sample.
4. Perform a rubout test to see if the Add produces a homogenous coating with reduced/no rubout.

Materials	Control	Sample 1	Sample 2
Incompatible Base	100.00	100.00	100.00
Borchi® Add 406WS	0.00	1.00	0.00
Borchi® Add 409WS	0.00	0.00	1.00
Total	0.00	101.00	101.00

PHASE 2

1. Add the best Borchi® Add product from Phase 1 into the incompatible system as a ladder at 1%, 2%, and 3%.
 - a. Below is a table of test formulations.
2. Mix/Agitate for 1 minute at 1500 rpm.
3. Drawdown the sample next to a control sample.
4. Perform a rubout test to see which level of Add produces the best coating with reduced/no rubout.

Materials	Control	Sample 3	Sample 4	Sample 5
Incompatible Base	100.00	100.00	100.00	100.00
Best Borchi® Add	0.00	1.00	2.00	3.00
Total	100.00	101.00	102.00	103.00

Contact us for more information

www.borchers.com/contact

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.