

Borchi® Gel 0626

TECHNICAL DATA

Non-ionic, polyurethane-based medium range thickener for water-based coatings systems, VOC-, APEO- and tin-free

FEATURES

- Develops viscosity stability and improves rheological properties mainly in the medium and high shear range
- Improved storage stability, leveling and application properties
- Does not yellow or cause chalking in the cured film
- VOC-free
- APEO-free
- Tin-free

PHYSICAL CHARACTERISTICS

Appearance	High-viscous liquid
Non-volatile content	34 - 38 % ISO 3251 (2g, 3h, 105 °C)
pH	5.5 - 7.5
Density	1.02 - 1.06 g/cm ³ DIN 53217 (23 °C)
Viscosity	Max. 10000 mPa.s ISO 3219 (A) (23 °C)
Solvent(s)	Water

APPLICATIONS

- Coatings
 - Brush and roller
 - E-Coat
 - General industrial
 - Automotive

Contact us for more information

www.borchers.com/contact

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.

DOSAGE

0.2 - 3.0% on total paint formulation

The best incorporation method is to add it after the pigment/filler dispersion stage but prior to being let down. Under low shear mixing conditions, a pre-dilution in water or a mixture of water/propylene glycol may be necessary for complete incorporation. The exact dosage should be experimentally determined.

STORAGE

Protect from the effects of weathering and store at temperatures between 5 and 30 °C. Once opened, containers should be resealed immediately after each removal of the product.

SAFETY

Please refer to our safety data sheet for information relating to product safety.