

Borchi® Nox 1640

TECHNICAL DATA

Special anti-skinning agent for coatings and printing inks

FEATURES

- Easy to incorporate
- Can be used in various binders still in the container
- Does not cause discoloration
- Does not adversely affect the drying time of the paint system
- Does not give rise to undesirable secondary phenomena during the drying process

PHYSICAL CHARACTERISTICS

Appearance	Clear, colorless to slightly turbid
Viscosity	Max. 50 mPa·s ISO 3219 (A) (20 °C)
Density	0.965 - 0.995g/cm ³ DIN 51757 (20 °C)
Solvent	NA

APPLICATIONS

- Printing inks
- Paints based on
 - Raw linseed oil
 - Wood oil
 - Maleic
 - Alkyd resins
 - Other comparable binders

DOSAGE

Borchi® Nox 1640 can directly be added in its supply form. It can be added either to the mill base or to the finished paint, stirring constantly. The addition of Borchi® Nox 1640 is 0.2 to 1.5 % on paint formulation or 1.5 - 2 times the amount of MEKO. The optimum dosage depends on the binder / pigment system and must be determined beforehand in trials.

STORAGE

Protect from the effects of weathering and store at temperatures between 5 and 30 °C. Once opened, containers should be resealed immediately after each removal of the product.

SAFETY

For further safety information please refer to our safety data sheet.

Contact us for more information

www.borchers.com/contact

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.