

# Borchi® Set 134

## TECHNICAL DATA

Thickener/suspending additive for solvent-based paints containing dense pigments

### FEATURES

- Anti-settling agent for solvent-based coatings
- Inhibits the hard settling of coatings containing dense pigments
- Easy to incorporate with high shear dispersing equipment
- Does not affect dry speed, hardness, gloss or weathering resistance of cured film

### PHYSICAL CHARACTERISTICS

Appearance	Greenish paste
Non-volatile content	55 - 60 % ISO 3251 (2g, 3h, 105 °C)
pH	NA
Density	0.94 - 0.98 g/cm <sup>3</sup> DIN 53217 (20 °C)
Viscosity	NA
Solvent(s)	White-spirit with < 1 % aromatics

### SAFETY

Please refer to our safety data sheet for information relating to product safety.

### Contact us for more information

[www.borchers.com/contact](http://www.borchers.com/contact)

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at [www.milliken.com/terms](http://www.milliken.com/terms) (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.

### APPLICATIONS

- Fillers
- Heavy pigments
- Metal powders
- Coatings
  - Epoxy
  - Epoxy ester
  - Alkyd
  - Chlorinated rubber
  - Vinyl resin polymers/ copolymers
  - Polyurethanes

### DOSAGE

1.0 - 3.0% on total paint formulation

Borchi® Set 134 can be added at any stage of the formulation although addition to the mill base is recommended. A high- speed mixer should be used for best incorporation into zinc-rich paints. The exact dosage should be experimentally determined

### STORAGE

Protect from the effects of weather and store at temperatures between 5 and 30 °C. Once opened, containers should be resealed immediately after each removal of the product.