

# Polidene® 33-083

Aqueous anionic copolymer emulsion specifically developed for use as a binder for water-based metal primers

### **Physical Characteristics**

Appearance	Creamy white
Non-volatile content	59.0 – 61.0 % 110 °C, 1h (Filter
	Papers)
рН	2.1 – 3.0
	neat, pH meter
Density	1.3 g/cm³, 25 °C
Viscosity*	30 - 70 mPa.s
MFFT	12 °C

<sup>\*</sup>Brookfield (25 °C) RV8, Spindle #1, 50 rpm

## **Features**

- Excellent barrier properties
- Properly formulated paints show excellent salt spray corrosion resistance
- APEO-free

## **Applications**

- Anti-corrosive primers
- Rust converters

## **Storage**

Protect from the effects of weathering and light. Store at temperatures between 5 and 30 °C. Once opened, containers should be resealed immediately after each removal of the product. Contact with common metals such as mild steel copper, zinc, or aluminum should be avoided.

#### Safety

Please refer to our safety data sheet for information relating to product safety.

811 Sharon Drive / Westlake, OH 44145 / Telephone: +1 800-321-9696 / 440-899-2950 / Fax: +1 440-808-7114 / Internet: www.borchers.com / E-Mail: info.us@borchers.com

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use, and processing of our products and the products manufactured by the customer based on our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Edition: 11/2019