

Borchi® Gol LAC 80

TECHNICAL DATA

Polyether-modified methyl polysiloxane, 100 % active

FEATURES

- Suitable for solvent-containing and solvent-free systems
- Brings about a clear increase in the surface smoothness of paint films
- Excellent flow promoter
- Prevents crater formation
- Largely prevents bleeding in hammer finishes
- Broad compatibility

PHYSICAL CHARACTERISTICS

Appearance	Liquid, yellow
Non-volatile content	NA
pH	NA
Density	1.020 - 1.026 g/cm ³ ISO 2811 (20 °C)
Viscosity	2000 - 2900 mPa.s DIN 53015 (23 °C)
Color	Hazen: Max. 700 ISO 6271
Refractive Index	1.437 - 1.441 DIN 51423 (23 °C)
Solvent(s)	NA

APPLICATIONS

- All coatings systems
- Aqueous binders and dispersions

Contact us for more information

www.borchers.com/contact

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.

DOSAGE

The recommended dosage is 0.05 % to 0.10 % Borchi® Gol LAC 80 relative to binder. To avoid incorrect dosages, we recommend that prior to incorporation a 10 % solution is prepared in a suitable solvent, e.g. in xylene for solvent-based paints and in propylene glycol for aqueous systems.

STORAGE

Protect from the effects of weathering and store at temperatures between 5 and 30 °C. Once opened, containers should be resealed immediately after each removal of the product to avoid exposure to water and atmospheric moisture as much as possible. Under no circumstances should the product be repacked from its original packaging container.

SAFETY

Please refer to our safety data sheet for information relating to product safety.