

## Borchi® Gol OL 44

Polyether modified polysiloxane for improved flow and slip properties in solvent- and water-based\* coatings systems, 100 % active, VOC-free

### Physical Characteristics

Appearance	Liquid, yellow
Non-volatile content	NA
pH	NA
Density	1.03 g/cm <sup>3</sup> DIN 51757 (20°C)
Viscosity	800 - 1000 mPa.s DIN 53015 (23 °C)
Color	Hazen: Max. 150 ISO 6271
Refractive Index	1.448 - 1.452 DIN 51423 (23 °C)
Solvent(s)	NA

### Features

- Eliminates craters and uneven film applications
- Increases and improves slip properties with no recoatability issues
- Very versatile with good efficiency in various baking enamels

### Applications

- Baking enamels based on
  - Alkyd resins
  - Alkyd / amino resin combinations
  - Acrylic resins
  - Acrylic / amino resin combinations

### Dosage

The recommended dosage is 0.05 % to 0.50 % of the total weight of the formulation depending upon the binder system. The exact dosage should be experimentally determined. No recoatability issues are expected when used at the recommended low addition rate levels. For solvent- and water-based\* systems.

### Storage

Protect from the effects of weathering and store at temperatures between 5 and 30 °C. Once opened, containers should be resealed immediately after each removal of the product to avoid exposure to water and atmospheric moisture as much as possible. Under no circumstances should the product be repacked from its original packing container

### Safety

Please refer to our safety data sheet for information relating to product safety.

**(\*) = recommendation for additional testing in water-based systems**

---

811 Sharon Drive / Westlake, OH 44145 / Telephone: +1 800-321-9696 / 440-899-2950 / Fax: +1 440-808-7114 / Internet: [www.borchers.com](http://www.borchers.com) / E-Mail: [info.us@borchers.com](mailto:info.us@borchers.com)

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at [www.milliken.com/terms](http://www.milliken.com/terms) (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.