

## Borchi® OXY-Coat 1310

Cobalt-free, metal-based catalyst which demonstrates excellent drying performance and other added benefits

### Physical Characteristics

Appearance	Clear brown to yellow liquid
Viscosity	Max. 100 mPa·s (informative) ISO 3219 (A) (20 °C)
Density	Approx. 0.97 g/cm <sup>3</sup> (informative) DIN 51757 (20 °C)
Solvent	Dipropylene glycol monomethyl ether (90%), 1,2-propylene glycol (9%) (informative)

### Features

- Improved drying activity, color performance, gloss and haze compared to cobalt-based driers
- Based on a unique, patented, highly active iron complex
- Recommended for solvent-based systems only
- Can be used in all coatings with binders that dry by oxidation
- Outperforms cobalt-based driers

### Applications

- Coatings with resins that dry by oxidation
  - Alkyds
  - Vegetable oils
  - Epoxy esters
  - Polybutadiene
  - Others

### Dosage

All resin systems are unique and will require the level of Borchi® OXY - Coat 1310 to be optimized for best cost and dry. We recommend starting at 0.5% of Borchi® OXY - Coat 1310 as supplied on resin solids to a maximum of 3%. Please keep in mind that too much Borchi® OXY - Coat 1310 might inhibit through dry. The Borchi® OXY - Coat 1310 should be added as one of the last ingredients before the Anti-Skinning agent.

### Storage

Protect from the effects of weathering and store at temperatures between 5 and 50 °C. Once opened, containers should be resealed immediately after each removal of the product.

### Safety

Please refer to our safety data sheet for information relating to product safety.

---

811 Sharon Drive / Westlake, OH 44145 / Telephone: +1 800-321-9696 / 440-899-2950 / Fax: +1 440-808-7114 / Internet: [www.borchers.com](http://www.borchers.com) / E-Mail: [info.us@borchers.com](mailto:info.us@borchers.com)

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use, and processing of our products and the products manufactured by the customer based on our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.