

Industrial Coatings

EU SF 1.2.

Water thinnable red two-pack PU topcoat,
based on Bayhydrol A 145 / Bayhydur 304

	Raw Material	Supplier	% by wt.
Component 1	Bayhydrol A 145	(1)	93.6
	Borchi® Gen 0851	(2)	2.1
	Borchi® Gel PW 25	(2)	0.3
	Surfynol 104 BC	(3)	2.0
	Irgazin® Red L 3660 HD	(4)	2.0
	<i>Total</i>		<i>100.0</i>
<i>Dispersion: 60 min, on Skandex BAS-20 in 250 ml screw-top jar with 200 g Zr-Silicate grinding beads</i>			
Component 2	Bayhydur 304	(1)	27.7
	Dipropylene glycol dimethyl ether	(5)	4.8
	<i>Total</i>		<i>32.5</i>
	<i>Incorporation: stir for approx. 5 min in a dissolver</i>		

Application Compressed-air spraying

Data		
NCO : OH - ratio		1.5 : 1
Ratio Comp. 1 : 2		3.1 : 1
Thinning with water		approx. 15 %
Spray viscosity, DIN 53211-cup 4mm, at 23 °C		approx. 30 s
Pot life		approx. 2 h
Drying	dust free tack free	approx. 30 min approx. 3 h
Haze and Gloss (20° angle), DIN 67530 / ISO 2813		20 / 86

Suppliers

- (1) Covestro (www.covestro.com)
- (2) Borchers (www.borchers.com)
- (3) Air Products (www.airproducts.com)
- (4) BASF (www.basf.com)
- (5) Clariant (www.clariant.com)

Berghausener Str . 100 / 40764 Langenfeld / Telephone: + 49 (0) 2173 - 39 26 666 Fax: +49 (0) 2173 - 39 26 999 / Internet:
www.borchers.com / E-Mail: info.info@borchers.com

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.