

## Decorative Paints

EU SF 6.7.

Clear varnish water thinnable,  
based on Resydrol VAY 6278w/45WA, VOC ≤ 1g/l

### Formulation

Raw Material	Supplier	% by
Resydrol VAY 6278w/45WA	(1)	90.1
Borchi® Gol LA 2	(2)	0.5
Borchi® Gel 0434	(2)	2.8
Defoamer		0.1
Water		6.5
<i>Total</i>		<i>100.0</i>

### Data

pH-value	evtl. adjust with AMP 90 to: 7.0 -	7.3
Viscosity Brookfield	Spindle 4 / 20 rpm; 20 °C	2300 mPas
Viscosity Krebs-Stormer	200 rpm; 20 °C	101 KU
Viscosity ICI	10.000 1/s	1.8 Poise
Density	20 °C	1.04 g/cm <sup>3</sup>
Gloss Gardner	20° / 60° angle (100 µm wet film thickness on	79 / 88
Drying time	Drying recorder; 23 °C (100 µm wet film thickness on	2 - 4 h
Solids content	1.5 h at 110 °C	ap. 41 %
VOC-content	DIN EN ISO 11890-1	< 1 g/l

### Suppliers

- (1) Allnex ([www.allnex.com](http://www.allnex.com))  
(2) Borchers ([www.borchers.com](http://www.borchers.com))

Berghausener Str. 100 / 40764 Langenfeld / Telephone: + 49 (0) 2173 - 39 26 666 Fax: +49 (0) 2173 - 39 26 999 / Internet:  
[www.borchers.com](http://www.borchers.com) / E-Mail: [info.info@borchers.com](mailto:info.info@borchers.com)

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at [www.milliken.com/terms](http://www.milliken.com/terms) (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.