

## Pigment concentrates

US SF 4.2.

### Binder free aqueous pigment concentrates

Pigment paste (Supplier)	A	B	C
<i>Color index</i>	<i>P.R. 122</i>	<i>P.Y. 74</i>	<i>P.B. 15:2</i>
Pigment Trade name (1)	Sunfast red 228-0641	Sunbrite Yellow 272-4608	Sunfast blue 248-615
Pigment	35	40	35
Borchi® Gen 0851 (2)	28	16	28
Water	36	43	36
Borchers® AF T (2)	1	1	1
<i>Total</i>	<i>100</i>	<i>100</i>	<i>100</i>
<b>Dosage of additive active content based on pigment content</b>	<b>40 %</b>	<b>20 %</b>	<b>40 %</b>

All indications are as supply form (in % by wt).

**Dispersion:** 60 min, on Skandex BAS-20, with 150 g Zr-Silicate grinding beads (2mm)

### Data

Particle size (using Grindometer)	< 6 µm	< 6 µm	< 7 µm
Viscosity (at shear rate 100 s <sup>-1</sup> ; 23 °C)	1250 mPa·s	280 mPa·s	280 mPa·s
Storage (2 weeks at 50 °C)	no significant alteration of the viscosity and particle size		

### Suppliers

- (1) Sun Chemical ([www.sunchemical.com](http://www.sunchemical.com))  
(2) Borchers Americas ([www.borchers.com](http://www.borchers.com))

811 Sharon Drive / Westlake, OH 44145 / Telephone: +1 800-321-9696 / 440-899-2950 / Fax: +1 440-808-7114 / Internet: [www.borchers.com](http://www.borchers.com) / E-Mail: [info.us@borchers.com](mailto:info.us@borchers.com)

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at [www.milliken.com/terms](http://www.milliken.com/terms) (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.