

## Pigment concentrates

EU SF 4.11.

Solvent borne pigment concentrates based on organic green pigments,  
containing Laropal A 81

Pigment paste	Supplier	A	B
Colour index		P.G. 7	P.G. 36
Pigment Trade name	(1)/(2)	Heliogen Green L8730	Sunfast Green 36
Pigment		23.0	23.0
Borchi® Gen 0755	(3)	7.8	8.0
Solvent mixture*		29.2	31.0
Laropal A 81, 60% in MPA	(1)	40.0	38.0
Total		100.0	100.0
<b>Dosage of additive active content based on pigment content</b>		<b>34.0 %</b>	<b>34.7 %</b>

All values are given as supply form (in % by wt).

\*Solvent mixture = methoxy propyl acetate / butyl acetate

**Dispersion:** 60 min, on Skandex Shaker, with 1.5 times Zr-silicate grinding beads (2mm)

### Data

Particle size	(using Grindometer)	< 15 µm
Viscosity	(at shear rate 100 s <sup>-1</sup> ; 23 °C)	< 1000 mPas
Storage stability	(2 weeks at 50 °C)	stable (no significant alteration of particle size and colour strength)

<b>Suppliers</b>	(1) BASF ( <a href="http://www.basf.com">www.basf.com</a> )
	(2) Sun Chemical ( <a href="http://www.sunchemical.com">www.sunchemical.com</a> )
	(3) Borchers ( <a href="http://www.borchers.com">www.borchers.com</a> )

Berghausener Str . 100 / 40764 Langenfeld / Telephone: + 49 (0) 2173 - 39 26 666 Fax: +49 (0) 2173 - 39 26 999 / Internet:  
[www.borchers.com](http://www.borchers.com) / E-Mail: [info.info@borchers.com](mailto:info.info@borchers.com)

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at [www.milliken.com/terms](http://www.milliken.com/terms) (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.