

## Pigment concentrates

EU SF 4.2.

### Aqueous pigment concentrates, binder free

Pigment paste	A	B	C
Colour index	P.R. 122	P.Y. 74	P.B. 15:2
Pigment Trade name (1)	Sunfast red 228-0641	Sunbrite Yellow 272-4608	Sunfast blue 248-615
Pigment	35	40	35
Borchi® Gen 0851 (2)	28	16	28
Water	36	43	36
Borchers® AF T (2)	1	1	1
Total	100	100	100
Dosage of additive active content based on pigment content	40 %	20 %	40 %

All indications are as supply form (in % by wt).

**Dispersion:** 60 min, on Skandex BAS-20, with 150 g Zr-Silicate grinding beads (2mm)

### Data

Particle size (using Grindometer)	< 6 µm	< 6 µm	< 7 µm
Viscosity (at shear rate 100 s <sup>-1</sup> ; 23 °C)	1250 mPa·s	280 mPa·s	280 mPa·s
Storage (2 weeks at 50 °C)	no significant alteration of the viscosity and particle size		

**Suppliers** (1) Sun Chemical ([www.sunchemical.com](http://www.sunchemical.com))  
(2) Borchers ([www.borchers.com](http://www.borchers.com))

Berghausener Str. 100 / 40764 Langenfeld / Telephone: + 49 (0) 2173 - 39 26 666 Fax: +49 (0) 2173 - 39 26 999 / Internet:  
[www.borchers.com](http://www.borchers.com) / E-Mail: [info.info@borchers.com](mailto:info.info@borchers.com)

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at [www.milliken.com/terms](http://www.milliken.com/terms) (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.