

## Pigment concentrates

## US SF 4.8.

Pigment concentrates for universal applications,  
based on COLOUR BLACK FW 200

### Formulation

Raw Material	Supplier	% By
<b>Borchi® Gen 0451</b>	(1)	12.0
Methoxy propyl acetate		73.0
COLOUR BLACK FW 200	(2)	15.0
<b>Total</b>		<b>100.0</b>
<i>Dispersion: 60 min, on Skandex BAS-20, with 150 g Zr-silicate grinding beads (2mm)</i>		

### Remarks

For aqueous systems applications can be additionally added butyl glycol.

### Data

Particle size (using Grindometer):	ca. 3 µm
Consistency:	free-flowing
Viscosity (at shear rate 100 s <sup>-1</sup> ; 23 °C):	750 mPa·s
Storage (2 weeks at 50 °C):	stable (no significant alteration of the viscosity and particle size)

### Testing of pigment paste in Binder formulations:

- Borchers - Formulation RR 5.1. (based on Bayhydrol A 145)

### Data

Haze and Gloss, DIN 67530 / ISO 2813	Haze	13
	Gloss Gardner (20° / 60° angle)	65 / 78

- Borchers - Formulation (based on Desmophen 2350)

### Data

Haze and Gloss, DIN 67530 / ISO 2813	Haze	10
	Gloss Gardner (20° / 60° angle)	85 / 91

### Suppliers

- (1) Borchers Americas ([www.borchers.com](http://www.borchers.com))
- (2) Orion Engineered Carbons ([www.orioncarbons.com](http://www.orioncarbons.com))

811 Sharon Drive / Westlake, OH 44145 / Telephone: +1 800-321-9696 / 440-899-2950 / Fax: +1 440-808-7114 / Internet: [www.borchers.com](http://www.borchers.com) / E-Mail: [info.us@borchers.com](mailto:info.us@borchers.com)

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at [www.milliken.com/terms](http://www.milliken.com/terms) (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.