

## Industrial Coatings

EU SF 1.10.

Glossy two-pack PU clear coat, fast drying, based on  
Setalux D A 870 BA / Desmodur N 3790

Component 1	Raw Material	Supplier	% by
	Setalux D A 870 BA	(5)	47.46
	Borchi® Gol OL 44*	(2)	0.20
	Tinuvin 292*	(3)	1.01
	Tinuvin 384-2, 50% in butyl acetate	(3)	2.02
	DBTL, 1% in xylene	(4)	1.55
	Xylene/butyl acetate/methoxy propyl acetate (1:1:1)		14.43
	<i>To be homogenised in a dissolver</i>		
Component 2	Desmodur N 3790, 90% in butyl acetate	(1)	19.53
	Additive TI	(2)	0.40
	Xylene/butyl acetate/methoxy propyl acetate (1:1:1)		13.40
	<b>Total</b>		<b>100.00</b>

\* 50% in xylene / butyl acetate / methoxy propyl acetate (1:1:1)

Mixing ratio of components 1 : 2 (by wt.) = 2 : 1

**Application** Spraying by means of pneumatic flow cup spray gun

Data	
Spray viscosity, DIN 53211-cup 4mm nozzle	20 s
Solids content on application	52.5 %
Pot life	approx. 2 h
Drying, DIN 53150; 23 °C; TG 1 sand-free:	30 min
Gloss Gardner (20°/60° angle), DIN 6730 / ISO 2813	90 / 93

**Suppliers**

- (1) Allnex ([www.allnex.com](http://www.allnex.com))
- (2) Borchers ([www.borchers.com](http://www.borchers.com))
- (3) BASF ([www.basf.com](http://www.basf.com))
- (4) Rhein-Chemie ([www.rheinchemie.com](http://www.rheinchemie.com))
- (5) Nuplex ([www.nuplex.com](http://www.nuplex.com))

Berghausener Str . 100 / 40764 Langenfeld / Telephone: + 49 (0) 2173 – 39 26 666 Fax: +49 (0) 2173 – 39 26 999 / Internet:  
[www.borchers.com](http://www.borchers.com) / E-Mail: [info.info@borchers.com](mailto:info.info@borchers.com)

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at [www.milliken.com/terms](http://www.milliken.com/terms) (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.