

## Anticorrosive coatings

EU SF 2.3.

Corrosion resistant water thinnable paint,  
based on Resydrol AZ 436w/45 WA, VOC ≤ 150g/l

### Formulation

	Raw Material	Supplier	% by
1.	Resydrol AZ 436w/45 WA	(1)	56,9
2.	Ammoniak, 10%ig		1,0
3.	Wasser		13,2
4.	Borchi® Gel 0626	(2)	3,0
5.	Surfynol SE-F	(3)	0,3
6.	Borchers® AF 1171	(2)	0,3
7.	Heucophos ZCPP	(4)	4,7
8.	Bayoxide® Z active	(2)	0,5
9.	Micro Talc AT extra	(5)	8,0
10.	Millicarb	(5)	5,2
11.	Bayferrox 130M	(6)	6,3
Pos. 1.-12. 30 min in der Perlmühle dispergieren.			
12.	Borchi® OXY-Coat 1101	(2)	0,15
13.	Ascinin® Anti Skin 0445	(2)	0,15
14.	AMP 90	(7)	0,3
Pos. 12. - 14. zugeben und 15 min. bei 500 U/min. rühren.			
	<b>Total</b>		<b>100,0</b>

### Technical Data

pH-value	8.5 – 9.3 (DIN 53875) evtl. adjust with	8.9
Viscosity Brookfield	Spindel 6/20 rpm; 20 °C	8500mPas
Viscosity Krebs-Stormer	200 rpm; 20 °C	115 KU
Pigment Volume Concentration		11.7%
Density	20 °C	1.26g/cm <sup>3</sup>
Solids-content	1.5 h at 125 °C	approx. 54 %
Drying	DIN 53150	TG1 – 15min. TG3 – 45min.
VOC-content (on)	DIN EN ISO 11890-1	approx. 150g/l
Cross-cuttest	DIN 52151 (after 1 week)	0 / 0

## Suppliers

- (1) Allnex ([www.allnex.com](http://www.allnex.com))
- (2) Milliken ([www.milliken.com](http://www.milliken.com))
- (3) Evonik ([www.evonik.com](http://www.evonik.com))
- (4) Heubach ([www.heubachinternational.de](http://www.heubachinternational.de))
- (5) Elementis ([www.elementis.com](http://www.elementis.com))
- (6) Lanxess ([www.lanxess.com](http://www.lanxess.com))
- (7) Angus Chemical ([www.angus.com](http://www.angus.com))

---

Berghausener Str . 100 / 40764 Langenfeld / Telephone: + 49 (0) 2173 – 39 26 666 Fax: +49 (0) 2173 – 39 26 999 / Internet:  
[www.borchers.com](http://www.borchers.com) / E-Mail: [info.info@borchers.com](mailto:info.info@borchers.com)

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at [www.milliken.com/terms](http://www.milliken.com/terms) (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.