

## Industrial Coatings

EU SF 1.18.

High glossy white water thinnable two-pack PU topcoat, rapidly drying, for metal, wood and plastic substrates, based on Synthalat WA 146 / Bayhydur 3100

	Raw Material	Supplier	A % by wt.	B % by wt.
Component 1	1. Synthalat WA 146, 42% in water/DMEA	(1)	67.5	67.5
	2. Borch <sup>®</sup> Gen 0851	(2)	2.0	2.0
	3. Surfynol 104 BC	(3)	0.5	0.5
	4. Borch <sup>®</sup> Gel 0625	(2)	0.3	–
	5. Borch <sup>®</sup> Gel Thix 921	(2) –		0.2
	6. Borch <sup>®</sup> Gol LA 232	(2)	0.4	0.4
	7. Sachtleben R-KB-4	(4)	18.0	18.0
	8. Water		11.3	11.4
	<i>Total</i>		<i>100.0</i>	<i>100.0</i>
<i>Place const.1. and add under mixing const. 2.-8. For 10 min. at 2000 rpm pre- dispersion, then dispersion for 35 min in bead mill. Let rest 1 day for deaeration.</i>				
Component 2	9. Bayhydur 3100	(5)	25.9	25.9
	10. Dipropylene glycol dimethyl ether		2.0	–
	11. Butoxyl (Methoxy butyl acetate)		–	2.0
	<i>Total</i>		<i>27.9</i>	<i>27.9</i>
	Water (for thinning)*		ap. 30 %	ap. 15 %
<i>Incorporation: stir for approx. 5 min in a dissolver</i>				

\* to adjust the spray viscosity

Application                      Compressed-air spraying

Data	A	B
NCO : OH - ratio	1.5:1	1.5:1
Spray viscosity, DIN 53211-cup 4mm, at 23 °C	ap. 30 s	ap. 25 s
Pendulum hardness, König method DIN EN ISO 1522 (100 µm wet film thickness on glass) after: 1 day / 3 days / 7 days	79/111/126	78/105/120
Haze and Gloss (20°/60°angle) DIN 67530 / ISO2813	6 / 85 / 92	6 / 86 / 93

Suppliers

- (1) Synthopol ([www.synthopol.com](http://www.synthopol.com))
- (2) Milliken ([www.milliken.com](http://www.milliken.com))
- (3) Evonik ([www.evonik.com](http://www.evonik.com))
- (4) Venator ([www.venatorcorp.com](http://www.venatorcorp.com))
- (5) Covestro ([www.covestro.com](http://www.covestro.com))

### borchers.com/contact

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at [www.milliken.com/terms](http://www.milliken.com/terms) (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.