

## Wood & Furniture Coatings

EU SF 3.15.

Glossy two-pack PU clear coat, fast drying, for spray application,  
based on Setalux D A 450 BA/X and Desmodur N 75

	Raw Material	Supplier	% by wt.
Component 1	Setalux D A 450 BA/X	(4)	54.0
	Butylacetate		14.0
	Borchi® Gol LAC 80, 50% in xylene / butyl acetate / methoxy propyl	(2)	0.3
	CAB 381-2, 25% in butyl acetate	(3)	12.0
	Methyl ethyl ketone		19.7
	<i>Total</i>		<i>100.0</i>
	<i>Homogenize in a dissolver</i>		
Component 2	Desmodur N 75, 75% in xylene / methoxy propyl	(1)	8.0

Data		
Comp.1: Comp. 2 - Mixing ratio		100 : 8
Solids content (Comp. 1), DIN EN ISO 3251		30 %
Solids content on application		30.5 %
Thinning for spray viscosity: xylene / butyl acetate (1:1)		10 %
Spray viscosity, DIN 53211-cup 4 mm, at 23 °C		ap. 24 s
Pot life		> 8 h
Drying TG 1 (sand dry), DIN 53150, at 23 °C		5 min
Hardness (König method), DIN EN ISO 1522 - after 1week		ap. 195 s
Gloss Gardner (20°/ 60° angle), DIN 67530 / ISO 2813		80 / 86
Haze		13
Chemical resistance, DIN 68861 part 1B (tested on beech wood veneered)		resistant

### Suppliers

- (1) Covestro ([www.covestro.com](http://www.covestro.com))
- (2) Milliken ([www.milliken.com](http://www.milliken.com))
- (3) Eastman Chemical ([www.eastman.com](http://www.eastman.com))
- (4) Allnex ([www.allnex.com](http://www.allnex.com))

### **borchers.com/contact**

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at [www.milliken.com/terms](http://www.milliken.com/terms) (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.