

## Pigment concentrates

EU SF 4.10.

Solvent borne pigment concentrates based on carbon black pigments,  
containing Laropal A 81

Pigment paste	Supplier	A	B
Color index		P.Bl. 7	P.Bl. 7
Pigment Trade name	(1)	Special Black 100	COLOUR BLACK FW 200
Pigment		28.00	14.55
Borchi® Gen 0755	(2)	10.00	11.65
Solvent mixture*		19.00	44.65
Laropal A 81, 60% in MPA	(3)	43.00	29.15
Total		100.00	100.00
Dosage of additive active content based on pigment content		35.7 %	80 %

All values are given as supply form (in % by wt).

\*Solvent mixture = methoxy propyl acetate / butyl acetate

**Dispersion:** 60 min, on Skandex Shaker, with 1.5 times Zr-silicate grinding beads (2mm)

### Data

Particle size (using Grindometer)	< 10 µm	
Viscosity (at shear rate 100 s <sup>-1</sup> ; 23 °C)	600 mPa·s	100 mPa·s
Storage stability (2 weeks at 50 °C)	<b>stable</b> (no significant alteration of particle size and color strength)	

**Suppliers**

- (1) Orion Engineered Carbons ([www.orioncarbons.com](http://www.orioncarbons.com))
- (2) Milliken ([www.milliken.com](http://www.milliken.com))
- (3) BASF ([www.basf.com](http://www.basf.com))

### [borchers.com/contact](http://borchers.com/contact)

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at [www.milliken.com/terms](http://www.milliken.com/terms) (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.