

## Automotive Coatings

EU SF 5.3.

Aqueous white two-pack PU topcoat,  
based on Bayhydrol A 145 and Bayhydur 304

	Raw Material	Supplier	% by wt.
Comp. 1	1. Bayhydrol A 145, 46%	(1)	40.2
	2. Surfynol 104 BC	(2)	0.9
	3. Borch <sup>®</sup> Gel PW 25	(3)	0.1
	4. Borch <sup>®</sup> Gol LA 200, 10% in butyl glycol	(3)	1.0
	5. Borch <sup>®</sup> Gen 0851	(3)	2.0
	6. Sachtleben R-KB-4	(4)	24.9
	<i>Total</i>		<i>69.1</i>
Comp. 2	7. Bayhydur 304	(1)	12.6
	8. Dipropylene glycol DME	(5)	3.1
	<i>Total</i>		<i>15.7</i>
	Water (for thinning)		15.2
	<i>Total</i>		<i>100.0</i>

### Indications

#### Formulation of topcoat comp. 1

Place const.1. in the mixing vessel. Stir in const. 2.-5.  
(10 min at 2000 rpm). Add gradually const.6. (at 2000 rpm).  
Pre-disperse for 10 min at 2000 rpm.  
Disperse in bead mill for 60 min (discontinuous < = 30°C)  
Leave to deaerate for one day.

### Application

Compressed-air spraying, nozzle 1.3 mm  
1 cross spraying, 5 min intermediate deaeration  
1 cross spraying, 10 min final deaeration

### Remarks

Light stabilizer to improve weather stability (add before component 2)  
1% Tinuvin 292 (solid / solid resin)

### Data

NCO :OH - ratio	1.5
Ratio comp. 1:2	4.52 : 1
Flow time, DIN 53211-cup 4 mm, at 23 °C	25 s
Cosolvent	7.6 %
Density	1.3 kg/l
VOC	118 g/l
pH-value	8.1
Solids content on application	58 %

## Technical properties

Viscosity increase: comp. (1+2) DIN 4 (s) / pH-value	0 h	25 / 8.1
	3 h	31 / 7.2
Drying 30 min 60 °C T1 / T3 (DIN 53150)	(0-5)*	2
	h	1 / 7
Pendulum hardness (s) DIN EN ISO 1522  (Substrate: glass)	1d RT	73
	7d RT	121
	16h 50°C	121
Film thickness	µm	50
Gloss 20° angle / visually (DIN 67530 / ISO 2813)		78 / 1
Haze (DIN 67530 / ISO 2813)		39

\* Evaluation: 0 = no visible changes  
5 = test surface was strongly changed respectively destroyed

## Chemical resistance:

Paint system on car body panel + conv. two-pack-PU primer (+ conv. basecoat for Formulation A and B)

H <sub>2</sub> O (1h)	immediately	4
	1d RT	1
	7d RT	1
	16h 50°C	1
5' premium gas / MPA / Xylene	immediately	4 4 4
	1d RT	1 2 2
	7d RT	1 1 1
	16h 50°C	1 1 1
Alkaline/acid** cleaning agent (1 h)		7d RT 0 / 0

\* Evaluation: 0 = no visible changes  
5 = test surface was strongly changed respectively destroyed

\*\* Alkaline = 2% sodium hydroxide solution  
Acid = 2% sulfuric acid

## Suppliers

- (1) Covestro ([www.covestro.com](http://www.covestro.com))
- (2) Air Products ([www.airproducts.com](http://www.airproducts.com))
- (3) Milliken ([www.milliken.com](http://www.milliken.com))
- (4) Sachtleben ([www.sachtleben.de](http://www.sachtleben.de))
- (5) Clariant ([www.clariant.com](http://www.clariant.com))

## [borchers.com/contact](http://borchers.com/contact)

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at [www.milliken.com/terms](http://www.milliken.com/terms) (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.