

Automotive Coatings

EU SF 5.5.

Water thinnable two-pack PU clear coat,
based on Bayhydrol A 145 and Bayhydur 304

	Raw Material	Supplier	% by wt.
Component 1	1. Bayhydrol A 145, 45%	(1)	48.3
	2. Surfynol 104 BC	(2)	1.1
	3. Borchi® Gel THIX 921	(3)	0.2
	4. Borchi® Gol LA 200 / Borchi® Gol LA 50 (3/7), 10%ig in BG	(3)	1.0
	<i>Total</i>		50.6
	<i>Place const.1. in the mixing vessel. Add under mixing const. 2.-4.; Mix further for 30 min. at 2000 rpm. Let rest 1 day for deaeration</i>		
Component 2	5. Bayhydur 304	(1)	15.1
	6. Butoxyl (Methoxy butyl acetate)		3.8
	<i>Total</i>		18.9
	Water (for thinning)*		30.5
	* to adjust the spray viscosity		
	<i>Total</i>		100.0
	Incorporation: stir for approx. 10 min in a dissolver		

Data	NCO : OH -ratio	1.5 : 1
	Spray viscosity, DIN 53211-cup 4mm, at 23 °C	approx. 20 s
	Pendulum hardness König method - DIN EN ISO 1522 (100 µm wet film thickness on glass) after: 1 day / 3 days / 7 days	120/150/160
	Haze and Gloss (20°/60°angle), DIN 67530 / ISO2813 (100 µm wet film thickness on ABS)	16 / 83 / 88

Suppliers	(1) Covestro (www.covestro.com)
	(2) Air Products (www.airproducts.com)
	(3) Milliken (www.milliken.com)

borchers.com/contact

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.