

Decorative Paints

EU SF 6.7.

Clear varnish water thinnable,
based on Resydrol VAY 6278w/45WA, VOC ≤ 1g/l

Formulation

Raw Material	Supplier	% by wt.
Resydrol VAY 6278w/45WA	(1)	90.1
Borchi® Gol LA 2	(2)	0.5
Borchi® Gel 0434	(2)	2.8
Defoamer		0.1
Water		6.5
<i>Total</i>		<i>100.0</i>

Data

pH-value	evtl. adjust with AMP 90 to: 7.0 - 8.5	7.3
Viscosity Brookfield	Spindle 4 / 20 rpm; 20 °C	2300 mPas
Viscosity Krebs-Stormer	200 rpm; 20 °C	101 KU
Viscosity ICI	10.000 1/s	1.8 Poise
Density	20 °C	1.04 g/cm ³
Gloss Gardner	20°/ 60° angle (100 µm wet film thickness on ABS)	79 / 88
Drying time	Drying recorder; 23 °C (100 µm wet film thickness on glass)	2 - 4 h
Solids content	1.5 h at 110 °C	ap. 41 %
VOC-content	DIN EN ISO 11890-1	< 1 g/l

Suppliers

- (1) Allnex (www.allnex.com)
(2) Milliken (www.milliken.com)

borchers.com/contact

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.