

Wood & Furniture Coatings

US SF 3.15.

High gloss 2K PU clear coat, based on Setalux D A 450 BA/X and Desmodur N 75

	Raw Material	Supplier	% by weight
Component 1	Setalux D A 450 BA/X	(4)	54.0
	Butylacetate		14.0
	Borchi® Gol LAC 80, 50% in xylol / butylacetate / methoxy propyl	(2)	0.3
	CAB 381-2, 25% in butyl acetate	(3)	12.0
	Methyl ethyl ketone		19.7
	<i>Total</i>		<i>100.0</i>
	<i>Homogenize in a dissolver</i>		
Component 2	Desmodur N 75, 75% in xylene / methoxy propyl	(1)	8.0

Formulation Parameters	Comp.1: Comp. 2 - Mixing ratio	100 : 8
	Solids content (Comp. 1), DIN EN ISO 3251	30 %
	Solids content on application	30.5 %
	Thinning for spray viscosity: xylene/butyl acetate (1:1)	10 %

Properties	Spray viscosity, DIN 53211-cup 4mm, at 23 °C	ap. 24 s
	Pot life	> 8 h
	Drying TG 1 (sand dry), DIN 53150, at 23 °C	5 min
	Hardness (König method), DIN EN ISO 1522 - after 1week	ap. 195 s
	Gloss Gardner (20°/ 60° angle), DIN 67530 / ISO 2813	80 / 86
	Haze	13
	Chemical resistance, DIN 68861 part 1B (tested on beech wood veneered)	resistant

Suppliers	(1) Covestro (www.covestro.com)
	(2) Milliken (www.milliken.com)
	(3) Eastman Chemical (www.eastman.com)
	(4) Allnex (www.allnex.com)

borchers.com/contact

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.