

22 % Zinc Hex-Cem®

TECHNICAL DATA

Zinc drier for solvent-based systems

FEATURES

- Keeps paint film “open” resulting in better through-drying of quick dry and baking systems
- Can prevent wrinkling and orange peel on paint film surface
- Improves pigment wetting and dispersion
- Can increase gloss and color fastness of coatings
- Grind times may be reduced
- Will not discolor paint film

PHYSICAL CHARACTERISTICS

Appearance	Light white liquid
Metal content	Zn: 22.00 - 23.00 %
Non-volatile content	>= 95.00 % ASTM D 1644
Viscosity	A-5 to Z-2 ASTM D 2373
Specific gravity	1.150 - 1.190 (25 °C) ASTM D 1963
Density	NA

APPLICATIONS

- Oxidatively cured solvent-based systems, including:
 - Architectural paints
 - Industrial coatings
 - Stains

Contact us for more information

www.borchers.com/contact

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.

DOSAGE

In conventional alkyd formulations, the Zinc addition is between 0.03 - 0.50 % metal based on the vehicle solids of the coating and will vary depending upon the composition of the binder. The specific drier blend should be experimentally determined. Zinc drier can be added to the dispersion and/or in the letdown with other driers.

STORAGE

Protect from the effects of weathering and store at temperatures below 50 °C. Once opened, containers should be resealed immediately after each use.

SAFETY

Please refer to our safety data sheet for information relating to product safety.