

7 % AOC E

TECHNICAL DATA

Aluminum drier for solvent-based systems

FEATURES

- Enhanced through dry
- Improved pigment wetting and dispersion
- Greater water resistance
- Improved yellowing resistance/less film discoloration
- Higher gloss retention
- Improved capacity
- Greater chalking resistance

PHYSICAL CHARACTERISTICS

Appearance	Dark yellow liquid
Metal content	Al: 6.70 - 7.30
Non-volatile content	50.00 - 70.00 % ASTM D 1644
Viscosity	A-5 to F ASTM D 2373
Specific gravity	0.960 - 1.061 (25 °C) ASTM D 1963
Density	NA

APPLICATIONS

High solids/thick film alkyd applications

DOSAGE

N/A

STORAGE

Protect from the effects of weathering and store at temperatures below 50 °C. Once opened, containers should be resealed immediately after each use.

SAFETY

Please refer to our safety data sheet for information relating to product safety.

Contact us for more information

www.borchers.com/contact

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.