

Dibutyltin Dilaurate

Catalyst for solvent-based two-component polyurethane systems

Physical Characteristics

Metal content	Sn: 18.2 - 18.9 %
Non-volatile content	>= 95.00 % ASTM D 1644
Viscosity	A-3 to C ASTM D 2373
Specific gravity	1.02 - 1.07 (25° C) ASTM D 1963
Density	NA

Features

- Suitable to accelerate the cross-linking process of solvent based two-component PU coatings
- Improves the drying of chemically curing systems favoring the isocyanate/polyol reaction over other side reactions such as isocyanate/water
- Enhances scratch resistance, hardness and mechanical properties
- Can be used to aid the curing process of polyurethanes, silicone resins, RTV silicone resins and silane modified polymers

Applications

- Solvent based, chemical cross-linking, two-component coating
 - o Polyurethane systems

Dosage

NA

Storage

Keep containers tightly closed in a dry, cool and well-ventilated place. Keep away from sources of ignition. Store in original container. Store in accordance with local regulations. Keep at temperatures between 5 °C and 30 °C.

Safety

Please refer to our safety data sheet for information relating to product safety.

811 Sharon Drive / Westlake, OH 44145 / Telephone: +1 800-321-9696 / 440-899-2950 / Fax: +1 440-808-7114 / Internet: www.borchers.com / E-Mail: info.us@borchers.com

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.