

Borchi® Gen AOD

TECHNICAL DATA

Adhesion promoter for improved adhesion to metal substrates

FEATURES

- Improved adhesion to non-ferrous metal surfaces that are difficult to adhere to, such as aluminum, aluminum alloys, zinc, stainless steel, etc.
- Can enhance the flexibility and impact resistance of the coating
- Does not influence the gloss and storage stability of the coating
- Improved chemical solvent resistance of polyester amino coatings

PHYSICAL CHARACTERISTICS

Appearance	Transparent Liquid
Solids Content	78-82%
Solvent(s)	Isopropanol

APPLICATIONS

- Solvent-Based Coatings
 - Coil coatings
 - Alkyd, polyester and acrylic baking systems
 - Other baking systems, please test first

Contact us for more information

www.borchers.com/contact

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.

DOSAGE

Add in the final process of coating production, with a dosage of 1% - 2% of the total formulation.

STORAGE

Protect from the effects of weathering and store at temperatures between 5 and 30 °C. Once opened, containers should be resealed immediately after each removal of the product.

SAFETY

Please refer to our safety data sheet for information relating to product safety.