

High glossy white water thinnable two-pack PU topcoat, rapidly drying, for metal, wood and plastic substrates, based on Synthalat WA 146 / Bayhydur 3100

	Raw Material	Supplier	A % by wt.	B % by wt.
Component 1	1. Synthalat WA 146, 42% in water/DMEA	(1)	67.5	67.5
	2. Borch [®] Gen 0851	(2)	2.0	2.0
	3. Surfynol 104 BC	(3)	0.5	0.5
	4. Borch [®] Gel 0625	(2)	0.3	–
	5. Borch [®] Gel Thix 921	(2) –		0.2
	6. Borch [®] Gol LA 232	(2)	0.4	0.4
	7. Sachtleben R-KB-4	(4)	18.0	18.0
	8. Water			11.3
	<i>Total</i>		<i>100.0</i>	<i>100.0</i>
<i>Place const. 1. and add under mixing const. 2.-8. For 10 min. at 2000 rpm pre- dispersion, then dispersion for 35 min in bead mill. Let rest 1 day for deaeration.</i>				
Component 2	9. Bayhydur 3100	(5)	25.9	25.9
	10. Dipropylene glycol dimethyl ether		2.0	–
	11. Butoxyl (Methoxy butyl acetate)		–	2.0
	<i>Total</i>		<i>27.9</i>	<i>27.9</i>
	Water (for thinning)*		ap. 30 %	ap. 15 %
<i>Incorporation: stir for approx. 5 min in a dissolver</i>				

* to adjust the spray viscosity

Application Compressed-air spraying

Data	A	B
NCO : OH - ratio	1.5 : 1	1.5 : 1
Spray viscosity, DIN 53211-cup 4mm, at 23 °C	ap. 30 s	ap. 25 s
Pendulum hardness, König method DIN EN ISO 1522 (100 µm wet film thickness on glass) after: 1 day / 3 days / 7 days	79/111/126	78/105/120
Haze and Gloss (20°/60°angle) DIN 67530 / ISO2813	6 / 85 / 92	6 / 86 / 93

Suppliers

- (1) Synthopol (www.synthopol.com)
- (2) Milliken (www.milliken.com)
- (3) Evonik (www.evonik.com)
- (4) Venator (www.venatorcorp.com)
- (5) Covestro (www.covestro.com)

borchers.com/contact

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.