

Industrial Coatings

EU SF 1.30.

Water thinnable two-pack PU clear coat / top coat (white),
based on Bayhydrol A 145 and Bayhydur 304

			A	B
			clear coat	white coat
Raw Material	Supplier	% by wt	% by wt	
Component 1	Bayhydrol A 145	(1)	48.30	40.20
	Surfynol 104 BC	(2)	1.10	0.90
	Borchi [®] Gel 0620	(3)	0.13	0.13
	Borchi [®] Gol LA 50	(3)	1.00	1.00
	Borchi [®] Gol LA 200 (7:3), 10% in butyl glycol			
	Borchi [®] Gen 0851	(3)	–	2.00
	Sachtleben R-KB-4	(4)	–	24.90
	Total		50.60	69.20
<i>Weigh in Bayhydrol A 145, add the additives under stirring and mix for about 10 min. at 2000 rpm; then disperse the pigment. Subsequently leave rest one day for defoaming.</i>				
Component 2	Bayhydur 304	(1)	15.10	12.60
	Dipropylene glycol dimethyl ether	(5)	3.80	3.10
	Total		18.90	15.70
	Water (for thinning)		30.57	15.17
Total		100.00	100.00	
<i>Incorporation: about 5 min in a dissolver</i>				

Application Compressed-air spraying

	A clear coat	B white coat
Data		
NCO : OH - ratio	1,5 : 1	1,5 : 1
Spray viscosity, DIN 53211-cup 4mm, at 23 °C	ap. 25 s	ap. 30 s
Solids content, 1,5 h / 110 °C	39 %	53 %
Density, at 20 °C	1.03 g/cm ³	1.24 g/cm ³
VOC-content, DIN ISO 11890-1	< 187 g/l	< 130 g/l
Pot life	> 7 h	> 6 h
Drying at room temperature	24 h 30 min	24 h 30 min
Pendulum hardness, (König method) DIN EN ISO 1522 (100 µm on glass)		
after 1 day	152 s	58 s
after 3 days	159 s	100 s
after 7 days	167 s	122 s
Haze and Gloss (60° angle), DIN 67530 / ISO 2813 (100 µm on glass)	18 / 79	24 / 86

Suppliers

- (1) Covestro (www.covestro.com)
- (2) Air Products (www.airproducts.com)
- (3) Milliken (www.milliken.com)
- (4) Venator (www.venatorcorp.com)
- (5) Clariant (www.clariant.com)

borchers.com/contact

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.