

Automotive Coatings

EU SF 5.4.

Aqueous two-pack PU clear coat,
based on Bayhydrol U XP 2766 / Bayhydur XP 2655

	Raw Material	Supplier	% by wt.
Component 1	1. Bayhydrol U XP 2766	(1)	64.10
	2. Borch ⁱ Gol LA 2	(2)	0.13
	3. Borch ⁱ Gol LA 50	(2)	0.17
	4. Borch ⁱ Gol LA 200	(2)	0.13
	5. Water		8.50
	<i>Total</i>		<i>73.03</i>

Component 2	6. Bayhydur XP 2655, 100%	(1)	17.84
	7. Tinuvin 384-2, 50% in Butoxyl	(3)	1.31
	8. Tinuvin 292, 50% in Butoxyl	(3)	0.87
	9. Butoxyl (methoxy butyl acetate)	(4)	6.95
	<i>Total</i>		<i>100.00</i>

Production indications

Formulationcomp. 1

Place const. 1. in the mixing vessel. Stir in successively const. 2.-4. (5 min at 2000 rpm). Add gradually const. 5. under stirring at approx. 2000 rpm. Leave to deaerate for one day.

Formulationhardener

Stir in successively const. 6.-9. at approx. 2000 rpm.

Mix components 1 and 2 for 2 minutes at 1000 rpm.

Add water to adjust the application viscosity.

Technical data

NCO : OH - ratio	1.5 : 1
Solid content on application (at 30 s application viscosity)	ap. 45 %
Spray viscosity, DIN 53211-cup 4 mm, at 23 °C component 1 + component 2 + approx. 10 %	25 s
VOC (calculated acc. Directive 1999/13/EC)	164 g/l
Gloss 20° / 60° (DIN EN ISO 2813) on ABS (Bayfoil)	92 / 95
Drying time (DIN 53150; at RT; TG 1 / TG 2 / TG 3)	0.5 / 3 / 4 h
Film Hardness (pendulum hardness tester-König) (DIN EN ISO 1522) (after 30 min 80 °C)	219 s

Suppliers

- (1) Covestro (www.covestro.com)
- (2) Milliken (www.milliken.com)
- (3) Ciba Specialty Chemicals (www.cibasc.com)
- (4) Celanese (www.celanese.com)

borchers.com/contact

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.