

Industrial Coatings

US SF 1.2.

2K PU red topcoat, based on Bayhydrol A 145 / Bayhydur 304

Component 1	Raw Material	Supplier	% By Weight
	Bayhydrol A 145	(1)	93.6
	Borchi [®] Gen 0851	(2)	2.1
	Borchi [®] Gel PW 25	(2)	0.3
	Surfynol 104 BC	(3)	2.0
	Irgazin [®] Red L 3660 HD	(4)	2.0
<i>Dispersion: 60 min, on Skandex BAS-20, in 250 ml screw-top jar with 200 g Zr-silicate grinding beads</i>			
	Total		100.0
Component 2	Bayhydur 304	(1)	27.7
	Dipropylene glycol dimethyl ether	(5)	4.8
	Total		32.5
<i>Incorporation: stir for approx. 5 min in a dissolver</i>			

Suggested Application Methods: spray

Formulation Parameters

NCO : OH - ratio	1.5 : 1
Ratio Comp. 1 : 2	3.1 : 1
Thinning with water	approx. 15 %

Properties

Spray viscosity (DIN 53211-cup 4mm, at 23 °C)	approx. 30 s
Pot life	approx. 2 h
Drying (dust free)	approx. 30 min
Drying (tack free)	approx. 3 h
Haze (DIN 67530)	20
Gloss (20° angle) (ISO 2813)	86

Suppliers

- (1) Covestro (www.covestro.com)
- (2) Milliken (www.milliken.com)
- (3) Evonik (www.evonik.com)
- (4) BASF (www.basf.com)
- (5) Clariant (www.clariant.com)

borchers.com/contact

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.